



Kester Wax K-82P (Hydroxy Polyester)

Kester Wax K-82P is a soft ester wax with properties similar to the complex polyester fraction of beeswax, the same fraction that gives beeswax its unique plastic properties.

Applications:

Lipsticks, Lip Balms, Creams, Lotions, Stick Pencils, Shave Creams, Mascaras, Make-ups, Color Concentrates, Extrusion Lubricants, Paints, Paraffin Modifiers, Printing Inks, Plastic Processing, Crayons.

Advantages:

Incorporating Kester Wax K-82P in sticks improves the film forming, adhesion, and plasticity. K-82P suppresses the crystallization of castor and other waxes. This high melting point wax is pliable at room temperature.

Regulatory:

INCI Name: C18-38 Alkyl Hydroxystearoyl Stearate CAS#: 151661-95-9

Wax#	Wax Name	Melting Point	Acid Value	Saponification Value	Ester Value	Color
358	Kester Wax K-24	23 - 30°C	<2	130 - 150	130 - 150	Off White to Yellow
352	Kester Wax K-385	40 - 50°C	<5	105 - 130	–	White to Light Tan
120, 177	Kester Wax K-48, Cetyl Esters	43 - 53°C	<5	109 - 125	–	White
254	Kester Wax K-56	54 - 57°C	<2	100 - 105	–	White
129	Kester Wax K-59	57 - 61°C	<2	97 - 104	–	White to Off White
484	Kester Wax K-60P	50 - 70°C	<10	90 - 125	–	Light Tan to Brown
130	Kester Wax K-62	60 - 65°C	<5	90 - 97	–	White to Light Yellow
176	Kester Wax K-64	62 - 65°C	<2	85 - 95	–	White to Light Yellow
131	Kester Wax K-72	70 - 74°C	<2	79 - 89	–	White to Light Yellow
167	Kester Wax K-82D	78 - 83°C	<5	–	50 - 70	Off White to Tan
124	Kester Wax K-82H	80 - 85°C	<6	72 - 96	70 - 90	Off White to Light Brown
154	Kester Wax K-82P (Hydroxy Polyester)	70 - 85°C	<10	50 - 90	–	Light Yellow to Light Brown
330	Kester Wax K-EM	79 - 85°C	<20	–	130 - 160	Light Yellow to Yellow
197	Branched Kester Wax BK-40	35 - 44°C	<15	65 - 83	50 - 82	White to Light Tan

Specific waxes that are most appropriate for this category have been highlighted here