

Balm for Vegan Leather

Features:

- **Ozokerite 70:** Excellent gelling agent and slip aid
- **Emulsifying Wax:** Emulsifier
- **Bayberry Wax:** Emollient, oil thickener, label claims

Formula#: 10/22-838/109-6

<i>Ingredient Trade Name</i>	<i>%</i>
<i>Phase A</i>	
Ozokerite 70¹	25.0
Emulsifying Wax¹	3.0
Bayberry Wax¹	3.0
Octocrylene	0.5
White Mineral Oil	43.5
Lilac Alkanes ²	25.0

Procedure:

- Combine all ingredients, melt and mix at 80-85 °C.
- Cool to 60 °C and pour into containers. Airtight containers are recommended.

Stability: One month at room temperature, one month at 45 °C, three freeze/thaw cycles.

Suppliers: 1. Koster Keunen, Inc.; 2. Sonneborn.